



Toll Free: 87 PERMATEX
(877-376-2839)

10 Columbus Blvd., Hartford,
Connecticut 06106

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

Permatex® Surface Insensitive Instant Adhesive

INDUSTRIAL

PRODUCT DESCRIPTION

S.I.N.: 834-300

Permatex® Surface Insensitive Instant Adhesive is a fast curing, single component ethyl cyanoacrylate designed specifically to assemble difficult-to-bond materials which require uniform stress distribution and strong shear adhesion. The product provides rapid bonding of a wide range of materials including plastic, metals, and elastomers.

TYPICAL APPLICATIONS

Permatex® Surface Insensitive Instant Adhesive is particularly suited for bonding porous materials such as wood, cork, paper, leather or fabric.

DIRECTIONS FOR USE

1. Protect the work surface against accidental spills, as cyanoacrylates can mark finishes and fabrics.
2. Clean and ensure a close fit on the surfaces to be bonded.
3. Apply the glue to one of the surfaces. Use sparingly, one square inch of surface area requires only one drop of glue.
4. Hold the surfaces to be bonded together for 15 to 30 seconds. No clamping is required. **DO NOT REPOSITION THE PARTS.**
5. Replace the cap, and store the adhesive in a cool spot.
6. Allow the parts to cure overnight.

For Cleanup

1. To remove Super Glue, use Super Glue Remover, acetone or nail polish remover that contains acetone.
2. To remove from hard surfaces such as Formica®, saturate a soft cloth or paper towel with the acetone and allow to rest on the spot for about 10 – 15 minutes. After the Super Glue is removed, a white or light colored spot may be left which is easily removed by applying mineral oil to the spot to restore the color.
3. Clean hands with acetone then use Permatex® brand hand cleaners.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Ethyl cyanoacrylate
Appearance	Clear liquid
Odor	Mild pungent
Specific Gravity	1.10
Flash Point, TCC, °F	>150

TYPICAL CURING PERFORMANCE

Under normal conditions, the surface moisture initiates the hardening process. Although full functional strength is developed in a relatively short time, curing will continue for at least 24 hours before full chemical/solvent resistance is developed.

Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved in different materials at 22°C, 50% relative humidity. This is defined as the time to develop a shear strength of 0.1 N/mm² (14.5 psi) tested on specimens per ASTM D1002.

Substrate	Fixture Time, seconds
Nitrile Rubber	<5
ABS	<10
PVC (plasticized)	5
Epoxy (G10)	<10
Steel	15
Aluminum	<5
Wood (Oak)	75

Cure Speed vs. Bond Gap

The rate of cure will depend on the bondline gap. High cure speed is favored by thin bond lines. Increasing the bond gap will slow down the rate of cure.

TYPICAL ENVIRONMENTAL RESISTANCE

Temperature Resistance	Typical Values
Continuous, °C (°F)	-54 to 82 (-65 to 180)
Tensile Strength, psi	1100 - 2525

Chemical / Solvent Resistance

The product retains effective properties when in contact with most solvents.

Aged 1000 hours under conditions indicated and tested at 22°C.

Environment	% of initial strength
Motor Oil	90
Gasoline	90
Ethanol	85
Isopropyl Alcohol	95
Heat/Humidity 95% RH	60
Heat Age 80°C	70

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
40140	20 gm bottle
40161	1 lb bottle

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8° to 28°C (46° to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications.