



Toll Free: 87 PERMATEX
(877-376-2839)

6875 Parkland Boulevard, Solon
Ohio 44139

Technical Data Sheet

Permatex® Steel Weld® Epoxy

AAM Revised 01/19

PRODUCT DESCRIPTION

Permatex® Steel Weld® epoxy is a premium two part, high strength, metal-filled epoxy adhesive system. Permatex® Steel Weld® epoxy can be drilled, threaded, and machined once fully cured. It repairs, fills and bonds most metal surfaces. It is resistant to most shop fluids including fuels, oil, water, and solvents. **NOTE: Permatex® Steel Weld® will not bond polyethylene and polypropylene plastics.**

PRODUCT BENEFITS

- Will not shrink
- No clamping needed
- Non-flammable
- Dark grey color
- Impact resistant
- Water resistant
- High temperature resistant
- Useable in 30 minutes

TYPICAL APPLICATIONS

- Aluminum
- Brass
- Chrome
- Copper
- Iron
- Stainless Steel
- Steel
- Zinc

DIRECTIONS FOR USE

1. Protect work area from accidental spills.
2. Surface must be clean, dry and free of grease & oil.
3. Slightly abrade the mating surfaces with sandpaper.
4. Remove the plastic tab from the tip of both nozzles.
5. Depress plunger on syringe or squeeze out of tubes equal amounts of resin and hardener. Thoroughly mix resin and hardener on a clean, disposable surface for at least one (1) minute or until uniform in color.
6. Apply to surfaces being repaired. Assemble parts immediately. Remove excess epoxy immediately.
7. Allow bond to set for the fixture time before handling or moving. Product fully cures in 24 hours.

For Cleanup

1. For any cleanup, use isopropyl alcohol before the material is allowed to dry.
2. Clean hands with Permatex® Fast Orange® hand cleaner or soap and water.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Epoxy and Mercaptan/Amine Resins
Mix Ratio	1:1

Appearance	Black
Resin	Off white/White
Hardener	Mild
Odor	1.75 - 1.85
Specific Gravity	>300°F
Flash Point, TCC	Paste
Viscosity	

USAGE PROPERTIES

	Working Time	Fixture Time
84109	4 – 5 minutes	8 – 10 minutes
84209	4 – 5 minutes	8 – 10 minutes

Final color	Grey
Temperature range	-60°F to +300°F(Continuous) +350°F(Intermittent)

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as an adhesive for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
84109	4 min. Multi-Metal Epoxy, 0.84 fl. oz. dual syringe, carded
84209	4 min. Multi-Metal Epoxy, 2 – 1oz. tubes, carded

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 46° to 82°F (8° to 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.**